

EZPRENE VU-320-70A

EZPRENE-V



Product Description :	This polyolefin based non-hygroscopic thermoplastic elastomer (TPE-V) compound is a dynamically vulcanized EPDM/PP blend with improved flow behaviour. EZPRENE® series are completely recyclable and can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Non-hygroscopic, no pre-drying Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range and low compression set Easy processing, faster cycle time over conventional TPVs Easy colorability with proper MB (PE, PP, etc)
Process Method :	Extrusion, coextrusion, blow molding, sheet extrusion, injection/multi injection molding
Uses :	Automotive, construction, home appliances, wire&cable, industrial applications
Revision Date :	01.05.2018

	Value	Unit	Standard
Physical			
Hardness	70	SHORE A	ISO 868 (3 second)
Density	0,97	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	2,3	Mpa	ISO 37, DIN 53504
300% Modulus	3,2	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	7,6	Mpa	ISO 37, DIN 53504
Elongation at Break	700	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	37	kN/m	ISO 34-1
Aging			
Compression Set (72h/23°C)	29	%	ISO 815
Compression Set (22h/70°C)	39	%	ISO 815
Compression Set (22h/100°C)	51	%	ISO 815

Environmental Resistance



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr

EZPRENE VU-320-70A

EZPRENE-V



Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr

EZPRENE VU-320-70A
EZPRENE-V



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr